




HONGER TECHNOLOGY (HK) LIMITED

Rm2103-2106, Hongfa Center Building, N5 District, Bao'an Center, Shenzhen, China.

EI 375



TOLERANCE: $\pm 0.08\text{mm}$

Unit in MM

K1 (STACKING FACTOR)

Thickness (mm)	Butt jointed	Interleaved one per layer
0.15	0.90	0.80
0.2	0.90	0.85
0.35	0.95	0.95

WEIGHT & PIECES

MATERIAL TYPE	THICKNESS (mm)	GRAMS/PIECE	PIECES/KG
PC (Ni 80%)			
	0.35	2.1030	476
PB (Ni 48%)			
	0.35	1.9820	505